

Technical Data Sheet

Filtration Products



Attributes & Properties ♦

Name: BG1560 / 985L INTREPID® Filtration Media

Color: White

Basis Weight: 3.6 ounces per square yard
(122 grams / square meter)

Efficiency: 75%
TSI Model 8130 automated filter tester with 0.1 µm count median diameter
NaCl particles at 85 liters per minute.

Air Permeability: 68 cubic feet of air/minute per square foot of media
(0.5 cubic meter of air / second meter of media)
Textest FX 3300

Thickness: 0.150 inches
(3.81 millimeters)
Testing load of 0.025 psi (172.4 Pascals)

Inside Core:
Diameter 6.75 inches
(171 millimeters)

♦ Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.

1400 Holcomb Bridge Road
Roswell, Georgia 30076-2199
Phone: 770-587-8000
www.kcprofessional.com





Technical Data Sheet

Filtration Products

Attributes & Properties ♦

BG1560Y / 985L INTREPID® Filtration Media page 2

=====

Roll Length: 180 linear yards
(165 linear meters)

Roll Diameter: 48 inches
(1.22 meters)

Slit Width Tolerance: +1/8, -1/8 inch
(+3 mm, - 3 mm)

Roll Labeling Information:

Slit Roll Label

Slit roll number
Product name and description
Production date
Basis weight
Slit width
Roll length
Roll weight
Country of origin

Powerpack Label

Powerpack number
Product name and description
Production date
Basis weight
Roll weight
Slit width
Total square yards in the powerpack
Total linear yards in the powerpack
Country of origin

Production Reference:

SPEC-12166

♦ Unless otherwise noted, the material described in this document is available for commercial sale and sold with a limited warranty. Kimberly-Clark Corporation and/or Kimberly-Clark Worldwide retains all intellectual property rights to this material, including trademarks and trade names. If the material described is defined as developmental, the material properties are estimates only and are not warranted by Kimberly-Clark Corporation.